



DOST KIMYA END. HAM. SAN. TIC. LTD. STI  
Istanbul Deri Organize San. Bolgesi Gerçef Sok.  
No : 6/B 34956 Tuzla / Istanbul

Tel : +90 (216) 429 0 999 PBX  
Fax : +90 (216) 429 0 888

## BOND300L- BOND300H

### LAMINASYON EPOKSI SISTEMI

#### Specification/ÖZELLİKLER

Approval/ ONAY	
Application/ UYGULAMA	production of boat and shipbuilding, sports equipment, model airplanes, molds and tools/ BOT, GEMİ, SPOR ALETLERİ, MODEL UÇAKLAR, KALIP VE GENEL UYGULAMALAR
Operational temperature/ CALISMA SICAK.	-60°C up to +50°C without heat treatment/ POSTKUR OLMADAN -60°C up to +80 C after heat treatment/POSTKUR ISLEMIYILE
Processing/ UYGULAMA SICAKLIGI	at temperatures between 10°C and 50°C all usual processing methods/ 10°C-50°C ARASINDA GENEL UYGULAMALARDA

#### Mixing ratios/KARIŞIM ORANLARI

	Laminating resin BOND300 Hardener BOND300H
parts by weight/ AGIRLIKCA	100 :50±2
parts by volume/ HACIMCE	100 :55±2

#### Gel time / JELLEŞME SÜRELERİ

	BOND300L Hardener BOND300H
20-25°C	app 2-3 hours/SAAT
40-45°C	app 45-60 mins/DAKIKA